

TEKAMID™ TA250G15

Polyamide 66

Mando Advanced Materials Co., Ltd.

Message:

TEKAMID™ TA250G15 is a Polyamide 66 (Nylon 66) product filled with 15% glass fiber. It is available in Asia Pacific. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm³	ASTM D792
Molding Shrinkage ¹			ASTM D955
Flow	0.50	%	
Across Flow	1.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	118	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	5490	MPa	ASTM D790
Flexural Strength	196	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	42	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	240	°C	
1.8 MPa, Unannealed	225	°C	
Peak Melting Temperature	260	°C	ASTM D2133
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	280 to 300	°C	
Mold Temperature	80.0 to 100	°C	
NOTE			

1. 60°C Mold Temperature

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

