

RTP ESD A 2180

Polyether Imide
RTP Company

Message:
Carbon Fiber - ESD Protection - Static Dissipative

General Information			
Filler / Reinforcement	Carbon fiber reinforced material		
Features	Electrostatic discharge protection		
	Static conduction		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.20 - 0.30	%	ASTM D955
Moisture Content	0.040	%	
Static Decay ¹		sec	FTMS 101C 4046.1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8270	MPa	ASTM D638
Tensile Strength	145	MPa	ASTM D638
Tensile Elongation (Yield)	3.0 - 5.0	%	ASTM D638
Flexural Modulus	6890	MPa	ASTM D790
Flexural Strength	207	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	53	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	530	J/m	ASTM D4812
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity			
--	1.0E+5 - 9.9E+11	ohms	ASTM D257
--	1.0E+4 - 9.9E+10	ohms	ESD STM11.11
Volume Resistivity	1.0E+3 - 9.9E+9	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	149	°C	
Drying Time	4.0	hr	
Dew Point	-28.9	°C	
Processing (Melt) Temp	354 - 399	°C	
Mold Temperature	135 - 177	°C	
Injection Pressure	82.7 - 124	MPa	
Injection instructions			

Desiccant Type Dryer Required.

NOTE

- | | |
|----|-------------------------------------|
| 1. | MIL-PRF-81705D, 5kV to 50 V, 12% RH |
|----|-------------------------------------|

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

