

REXtac® APAO RT 2732

Polyalphaolefin

Huntsman Corporation

Message:

Butene-1 copolymer

General Information			
Features	Copolymer		
	amorphous		
	Medium viscosity		
Uses	Sealant		
	Adhesive		
Agency Ratings	FDA 21 CFR 175.105		
RoHS Compliance	Contact manufacturer		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.870	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	0.590	MPa	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-22.0	°C	DSC
Fill Analysis	Nominal Value	Unit	
Melt Density (190°C)	0.750	g/cm ³	
Additional Information			

Melt Viscosity, ASTM D3236, 250°F: 54900 cpsMelt Viscosity, ASTM D3236, 275°F: 15600 cpsMelt Viscosity, ASTM D3236, 300°F: 9600 cpsMelt Viscosity, ASTM D3236, 325°F: 6300 cpsMelt Viscosity, ASTM D3236, 350°F: 4500 cpsMelt Viscosity, ASTM D3236, 375°F: 3000 cpsMelt Viscosity, ASTM D3236, 400°F: 2400 cpsNeedle Penetration, ASTM D1321, 25°C: 2.2 mmSoftening Point by Ring and Ball, ASTM E28: 247°FShear Adhesion Failure Temp. (SAFT), Kraft/Kraft, Huntsman Method: 248°FOpen Time, Kraft/Kraft, 25°C, Huntsman Method: 120 secondsFlashpoint, COC, ASTM D93: >450°F

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT