

Infino SA-1100

Polycarbonate

LOTTE ADVANCED MATERIALS CO., LTD.

Message:

Infino SA-1100 is a polycarbonate (PC) product. It is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: electrical/electronic applications. The main characteristics are: flame retardant/rated flame.

General Information			
UL YellowCard	E115797-100736961		
Features	General		
Uses	Switch		
Physical	Nominal Value	Unit	Test Method
Specific Gravity (Natural)	1.20	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	9.0	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow: 3.20mm	0.46 - 0.56	%	ASTM D955
Transverse flow: 3.20mm	0.48 - 0.58	%	ASTM D955
Lateral flow: 3.20mm	0.48 - 0.58	%	ISO 2577
Traffic: 3.20mm	0.46 - 0.56	%	ISO 2577
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
Class r	120		ASTM D785
R scale	120		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2000	MPa	ASTM D638
--	2050	MPa	ISO 527-2/50
Tensile Strength			
Yield ²	64.0	MPa	ASTM D638
Yield	63.0	MPa	ISO 527-2/50
Fracture ³	66.0	MPa	ASTM D638
Fracture	70.0	MPa	ISO 527-2/50
Tensile Elongation			
Fracture ⁴	91	%	ASTM D638
Fracture	90	%	ISO 527-2/50
Flexural Modulus			
-- ⁵	2300	MPa	ASTM D790
-- ⁶	2260	MPa	ISO 178
Flexural Strength			
-- ⁷	96.0	MPa	ASTM D790

-- ⁸	90.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	70	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C, 3.18 mm	690	J/m	ASTM D256
23°C, 6.35 mm	200	J/m	ASTM D256
23°C ¹⁰	70	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 6.40mm	127	°C	ASTM D648
1.8 MPa, not annealed, 4.00mm	125	°C	ISO 75-2/A
Vicat Softening Temperature	142	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (CTI)	PLC 3		IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.5 to 3.0mm)	V-2		UL 94
Glow Wire Ignition Temperature (1.5 mm)	875	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature			
--	110	°C	
Hot air dryer	110	°C	
Drying Time			
--	4.0	hr	
Hot air dryer	4.0	hr	
Suggested Max Moisture	0.020 - 0.030	%	
Rear Temperature	240 - 250	°C	
Middle Temperature	260 - 270	°C	
Front Temperature	280 - 285	°C	
Nozzle Temperature	290	°C	
Mold Temperature	50 - 80	°C	
Injection Pressure	68.6 - 206	MPa	
Back Pressure	0.490	MPa	
Screw Speed	30	rpm	
Injection instructions			
Hot Runner Manifold Temperature: 280°C Hot Runner Valve Nozzle Temperature: 280°C			
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	50 mm/min		
5.	2.8 mm/min		
6.	2.0 mm/min		

7.	2.8 mm/min
8.	2.0 mm/min
9.	Thickness: 4mm
10.	Thickness: 4mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

