Matrixx 12N4010

Polypropylene

The Matrixx Group, Inc.

Message:

Matrixx 12N4010 is a polypropylene material. This product is available in North America. The main features of Matrixx 12N4010 are:

flame retardant/rated flame

Flame Retardant

| General Information | | | |
|---|------------------|----------|-------------|
| Additive | Flame retardancy | | |
| Features | Flame retardancy | | |
| Forms | Particle | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.928 | g/cm³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (230°C/2.kg) | 8.0 | g/10 min | ASTM D1238 |
| Molding Shrinkage - Flow | 1.6 - 2.2 | % | ASTM D955 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Yield) | 34.5 | MPa | ASTM D638 |
| Flexural Modulus | 1450 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact | 27 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (MPa, Unannealed) | 0.45 96.1 | °C | ASTM D648 |
| RTI Elec | 110 | °C | UL 746 |
| RTI Imp | 110 | °C | UL 746 |
| RTI | 110 | °C | UL 746 |
| Flammability | Nominal Value | | Test Method |
| Flame Rating (1.50 mm) | V-2 | | UL 94 |
| Additional Information | | | |

The value listed as Mold Shrinkage, ASTM D955, was tested in accordance with Matrixx test methods.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

