

AIE PC/ABS A2200FR-3070

Polycarbonate + ABS

Asia International Enterprise (Hong Kong) Limited

Message:

AIE PC/ABS A2200FR-3070 is a Polycarbonate + ABS (PC+ABS) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of AIE PC/ABS A2200FR-3070 are:

- Flame Rated
- RoHS Compliant
- Flame Retardant

General Information			
Features	Flame Retardant		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	12	g/10 min	ISO 1133
Molding Shrinkage	0.50 to 0.80	%	Internal Method
Water Absorption (23°C, 24 hr)	0.30	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	56.0	MPa	ISO 527-2
Tensile Strain (Break)	63	%	ISO 527-2
Flexural Modulus	2000	MPa	ISO 178
Flexural Stress	82.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	46	kJ/m²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	100	°C	ISO 75-2/B
1.8 MPa, Unannealed	88.0	°C	ISO 75-2/A
Flammability	Nominal Value	Test Method	
Flame Rating (1.50 mm)	V-0	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	3.0 to 4.0	hr	
Processing (Melt) Temp	220 to 260	°C	
Mold Temperature	80.0 to 110	°C	
Injection Pressure	40.0 to 100	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

