

Pibiter® NRV30 NAT001

Polybutylene Terephthalate

SO.F.TER. SPA

Message:

30% glass fiber reinforced PBT grade

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Agency Ratings	EC 1907/2006 (REACH)		
UL File Number	E187982		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.52	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	14	g/10 min	ASTM D1238
Molding Shrinkage	0.35	%	Internal Method
Water Absorption			
23°C, 24 hr	0.040	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.25	%	ISO 62
Ash Content	30	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9800	MPa	ASTM D638
Tensile Strength (Break)	130	MPa	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638
Flexural Modulus	9000	MPa	ASTM D790
Flexural Strength	210	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	85	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	220	°C	
1.8 MPa, Unannealed	210	°C	
Vicat Softening Temperature	215	°C	ASTM D1525 ¹
CLTE - Flow	2.5E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	ASTM D257
Volume Resistivity (23°C)	1.0E+15	ohms · cm	ASTM D257
Dielectric Strength (1.60 mm)	22	kV/mm	ASTM D149
Dielectric Constant (1 kHz)	3.80		ASTM D150

Dissipation Factor (1 kHz)	3.0E-3		ASTM D150
Comparative Tracking Index	350	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.750 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Rear Temperature	235	°C	
Middle Temperature	250	°C	
Front Temperature	260	°C	
Mold Temperature	70.0 to 100	°C	
NOTE			
1.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT