

KOPET® KP133G15BU

Polyethylene Terephthalate

Kolon Plastics, Inc.

Message:

KOPET® KP133G15BU is a Polyethylene Terephthalate (PET) product filled with glass fiber. It is available in Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

Flame Rated

Good Dimensional Stability

High Flow

General Information	
UL YellowCard	E190675-100642742
Filler / Reinforcement	Glass Fiber
Features	Good Dimensional Stability
	High Elasticity
	High Flow

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.45	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 60% RH)	0.10	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	98.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	6.0	%	ASTM D638
Flexural Modulus (23°C)	5390	MPa	ASTM D790
Flexural Strength (23°C)	152	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	34	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648A
0.45 MPa, Unannealed	235	°C	
1.8 MPa, Unannealed	185	°C	
Peak Melting Temperature	255	°C	ASTM D3418
CLTE - Flow	4.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	19	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.70		ASTM D150
Arc Resistance	119	sec	ASTM D495

Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

