

Ultramid® N-276 NF3001

Polyamide 66

BASF Corporation

Message:

Ultramid N-276 NF3001 is a 40% mineral/glass reinforced, heat stabilized injection molding PA6/6.

General Information			
UL YellowCard	E36632-317040		
Filler / Reinforcement	Glass\Mineral,40% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.50	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	10800	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	135	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	3.0	%	ISO 527-2
Flexural Modulus (23°C)	9800	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	3.5	kJ/m ²	
23°C	3.8	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-30°C	40	kJ/m ²	
23°C	45	kJ/m ²	
Notched Izod Impact Strength (23°C)	4.2	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	255	°C	ISO 75-2/B
1.8 MPa, Unannealed	242	°C	ISO 75-2/A
Melting Temperature (DSC)	260	°C	ISO 3146
Injection	Nominal Value	Unit	
Drying Temperature	60.0	°C	
Drying Time	1.0 to 2.0	hr	
Suggested Max Moisture	0.040 to 0.20	%	
Processing (Melt) Temp	288 to 305	°C	

Mold Temperature	60.0 to 100	°C
Injection Pressure	3.50 to 12.5	MPa
Injection Rate	Fast	
Back Pressure	0.00 to 0.350	MPa
Screw Speed	40 to 80	rpm
Screw Compression Ratio	3.0:1.0 to 4.0:1.0	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

