# Favorite LL515

## Low Density Polyethylene + LLDPE

### **Favorite Plastics**

### Message:

LL515 is a blend of LDPE and LLDPE haviing properties which incorporates some advantages of each resin type. End uses include shopping bags, other soft goods bags and laminations.

General Information			
Uses	Laminate		
	Bags		
Forms	Films		
Physical	Nominal Value	Unit	Test Method
Density	0.922	g/cm³	ASTM D1505
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction	0.16		ASTM D1894
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	32	μm	
Tensile Strength - MD (Break, 32 µm)	21.9	MPa	ASTM D882
Tensile Elongation - MD (Break, 32 $\mu$ m)	680	%	ASTM D882
Dart Drop Impact (32 µm)	160	g	ASTM D1709
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 31.8 µm)	66		ASTM D2457
Haze (31.8 µm)	9.0	%	ASTM D1003
Additional Information			

Coefficient of Friction, ASTM D1894: <0.16

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

