

# Lupolen 2420 K

Low Density Polyethylene

LyondellBasell Industries

## Message:

Lupolen 2420 K is a non-additivated, low density Polyethylene. It is delivered in pellet form. Foodlaw compliance information about this product can be found in separate product documentation.

General Information	
Features	Optical Workability, good
Uses	Films Protective coating cast film Food packaging Shrinkable film Coating application
Forms	Particle
Processing Method	Blow film Extrusion coating cast film Injection molding

Physical	Nominal Value	Unit	Test Method
Density	0.924	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.0	g/10 min	ISO 1133

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	260	MPa	ISO 527-2
Tensile Stress (Yield)	11.0	MPa	ISO 527-2
Coefficient of Friction (Blown Film)	> 0.70		ISO 8295

Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	50	µm	
Film Thickness - Recommended / Available	0.6-1.6 mil (15-40 µ)		
Tensile Strength			ISO 527-3
MD: 50 µm, blown film	22.0	MPa	ISO 527-3
TD: 50 µm, blown film	17.0	MPa	ISO 527-3
Tensile Elongation			ISO 527-3
MD: Broken, 50 µm, blown film	300	%	ISO 527-3
TD: Broken, 50 µm, blown film	600	%	ISO 527-3

Dart Drop Impact (50 µm, Blown Film)	100	g	ASTM D1709
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Vicat Softening Temperature	92.0	°C	ISO 306/A50
Melting Temperature (DSC)	111	°C	ISO 3146
<b>Optical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Gloss			ASTM D2457
20, 50.0 µm, blown film	> 60		ASTM D2457
60, 50.0 µm, blown film	> 105		ASTM D2457
Haze (50.0 µm, Blown Film)	< 8.0	%	ASTM D1003
<b>Additional Information</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Failure Energy - Blown Film (50.0 µm)	35.0	J/cm	DIN 53373
Film properties tested using 50 µm thickness blown film extruded at a melt temperature of 170°C and a blow-up ratio of 1:2.5.			
<b>Extrusion</b>	<b>Nominal Value</b>	<b>Unit</b>	
Melt Temperature	150 - 190	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

