

PRL NY66-GP1-(color)H

Polyamide 66
Polymer Resources Ltd.

Message:

PRL NY66-GP1-(color)H is a Polyamide 66 (Nylon 66) product. It can be processed by injection molding and is available in North America.
Characteristics include:
Flame Rated
RoHS Compliant
Heat Stabilizer
Lubricated

General Information			
Additive	Heat Stabilizer		
	Lubricant		
Features	General Purpose		
	Heat Stabilized		
	Lubricated		
RoHS Compliance	RoHS Compliant		
UL File Number	E113219		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.2 to 1.8	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 3.18 mm	82.7	MPa	
Break, 3.18 mm	82.7	MPa	
Flexural Modulus (3.18 mm)	3100	MPa	ASTM D790
Flexural Strength (3.18 mm)	117	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	229	°C	
1.8 MPa, Unannealed, 3.18 mm	87.8	°C	
RTI Elec			UL 746
1.50 mm	65.0	°C	
3.00 mm	65.0	°C	
RTI Imp			UL 746

1.50 mm	65.0	°C
3.00 mm	65.0	°C
RTI Str		UL 746
1.50 mm	65.0	°C
3.00 mm	65.0	°C
Flammability	Nominal Value	Test Method
Flame Rating		UL 94
1.50 mm	V-2	
3.00 mm	V-2	
Injection	Nominal Value	Unit
Drying Temperature	73.9 to 85.0	°C
Drying Time	3.0 to 4.0	hr
Drying Time, Maximum	8.0	hr
Rear Temperature	266 to 277	°C
Middle Temperature	271 to 282	°C
Front Temperature	277 to 288	°C
Processing (Melt) Temp	277 to 293	°C
Mold Temperature	65.6 to 93.3	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

