

Marlex® PP HGZ-350SP

Polypropylene Homopolymer

Saudi Polymers Company

Message:

Typical injection moulding applications include:

Thin wall containers

Toys

Hospital ware

Good resistance to gas fading

General Information			
Features	Homopolymer		
	Resistance to gas fading		
	Controlled rheology		
	Compliance of Food Exposure		
Uses	Thin wall container		
	Toys		
	Medical equipment		
Agency Ratings	FDA not rated		
	Europe No 10/2011		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.903	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	35	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (shaw d, 3.20mm, injection molding)	71		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm, Injection Molded)	40.0	MPa	ASTM D638
Flexural Modulus - Secant ² (3.20 mm, Injection Molded)	1790	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm, Injection Molded)	21	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 3.20 mm, Injection Molded)	113	°C	ASTM D648

Additional Information

Mechanical properties were determined using injection-moulded specimens 3.2 mm thick, moulded per ASTM D4101, unless otherwise noted.

NOTE

- | | |
|----|------------|
| 1. | 51 mm/min |
| 2. | 1.3 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

