

Petrothene® GA502022

Linear Low Density Polyethylene

LyondellBasell Industries

Message:

The Petrothene GA502 series of resins are pelletized linear low density polyethylenes for applications requiring excellent drawdown and toughness. These pelletized products offer excellent additive homogeneity, require no transfer equipment modification and facilitate clean and safe storage and handling. They can be used in either blown or cast film extrusion.

General Information	
Additive	Antiblock (7000 ppm) Slip (1350 ppm)
Features	Antiblocking Food Contact Acceptable Good Drawdown Good Toughness Slip
Uses	Cast Film Film
Agency Ratings	FDA 21 CFR 177.1520
Forms	Pellets
Processing Method	Blown Film Cast Film Film Extrusion

Physical	Nominal Value	Unit	Test Method
Density	0.918	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	38	µm	
Secant Modulus			ASTM D882
1% Secant, MD : 38 µm	221	MPa	
1% Secant, TD : 38 µm	248	MPa	
Tensile Strength			ASTM D882
MD : Break, 38 µm	33.8	MPa	
TD : Break, 38 µm	24.8	MPa	
Tensile Elongation			ASTM D882
MD : Break, 38 µm	750	%	

TD : Break, 38 µm	800	%	
Dart Drop Impact (38 µm, Blown Film)	120	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 38 µm	170	g	
TD : 38 µm	400	g	
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 38.1 µm, Blown Film)	60		ASTM D2457
Haze (38.1 µm, Blown Film)	12	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Melt Temperature	191 to 218	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

