

Durethan® BKV 35 XTS1 901510

Polyamide 6

LANXESS GmbH

Message:

PA 6, 35 % glass fibers, injection molding, heat-aging stabilized, notably high heat-aging stability

General Information			
Filler / Reinforcement	Glass Fiber,35% Filler by Weight		
Additive	Heat Stabilizer		
Features	Good Heat Aging Resistance		
	Heat Stabilized		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.41	g/cm ³	ISO 1183
Molding Shrinkage			ISO 2577
Across Flow : 280°C, 2.00 mm ¹	0.73	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.91	%	
Flow : 280°C, 2.00 mm ³	0.23	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.30	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	10700	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	180	MPa	ISO 527-2/5
Nominal Tensile Strain at Break (23°C)	3.0	%	ISO 527-2/50
Flexural Modulus ⁵ (23°C)	10400	MPa	ISO 178/A
Flexural Stress ⁶ (23°C)	270	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	3.4	%	ISO 178/A
ISO Shortname	PA 6, GHR, 14-110, GF35		ISO 1874
Residual Moisture Content	0.030 to 0.12	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	8.0	kJ/m ²	
23°C	10	kJ/m ²	
Charpy Unnotched Impact Strength (23°C)	70	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength (23°C)	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	70	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	205	°C	ISO 75-2/A
Melting Temperature ⁸	221	°C	ISO 11357-3

CLTE		ISO 11359-2	
Flow : 23 to 55°C	1.7E-5	cm/cm/°C	
Transverse : 23 to 55°C	1.0E-4	cm/cm/°C	
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Dry Air Dryer	80.0	°C	
Drying Time - Dry Air Dryer	2.0 to 6.0	hr	
Processing (Melt) Temp	250 to 290	°C	
Mold Temperature	80.0 to 100	°C	
NOTE			
1.	60x60x2mm, 80°C MT, 600 bar		
2.	60x60x2mm		
3.	60x60x2mm, 80°C MT, 600 bar		
4.	60x60x2mm		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	2 mm/min		
8.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

