

# SABIC® HDPE CC3054

High Density Polyethylene Copolymer

Saudi Basic Industries Corporation (SABIC)

## Message:

SABIC® HDPE CC3054 is a high density polyethylene copolymer injection moulding grade. Its narrow molecular weight distribution and high flow results in low warpage, good rigidity, good gloss and fast moulding cycles.

SABIC® HDPE CC3054 is typically used for caps and closures applications and thin wall articles.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

General Information			
Features	Copolymer		
	Fast Molding Cycle		
	High Density		
	High Flow		
	Low Warpage		
	Medium Gloss		
	Medium Rigidity		
	Narrow Molecular Weight Distribution		
Uses	Caps		
	Closures		
	Thin-walled Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.954	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	30	g/10 min	ISO 1133
Environmental Stress-Cracking Resistance <sup>1</sup> (60°C, 3.00 mm, Rhodacal-DS10, Compression Molded)	40.0	hr	Internal Method
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, Compression Molded)	61		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (2.00 mm, Compression Molded)	1100	MPa	ISO 527-2/1BA/50
Tensile Stress			ISO 527-2/1BA/50
Yield, 2.00 mm, Compression Molded	26.0	MPa	
Break, 2.00 mm, Compression Molded	25.0	MPa	
Tensile Strain (Break, 2.00 mm, Compression Molded)	> 200	%	ISO 527-2/1BA/50

Flexural Modulus (2.00 mm, Compression Molded)	1250	MPa	ISO 178
Flexural Stress (2.00 mm, Compression Molded)	27.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C, Compression Molded)	3.0	kJ/m <sup>2</sup>	ISO 180/A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	82.0	°C	ISO 75-2/B
Vicat Softening Temperature	125	°C	ISO 306/A
Melting Temperature (DSC)	132	°C	ISO 11357-3
Enthalpy Change	205	J/g	ISO 11357-3
NOTE			
1.	2 MPa		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

