

ALTECH® PA66 ECO 2005/500

Polyamide 66

ALBIS PLASTIC GmbH

Message:

ALTECH®PA66 ECO 2005/500 is a polyamide 66 (nylon 66) product that contains 5.0% glass fiber reinforcement. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region. ALTECH®The application fields of PA66 ECO 2005/500 include engineering/industrial accessories and automobile industry.

Features include:

flame retardant/rated flame

Comply with REACH standard

environmental protection/green

ROHS certification

Impact modification

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 5.0% filler by weight		
Additive	Impact modifier		
Recycled Content	Yes		
Features	Impact modification		
Uses	Pump parts		
	Machine/mechanical parts		
	Accessories		
	Application in Automobile Field		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (275°C/5.0 kg)	60.0	cm³/10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3000	MPa	ISO 527-2
Tensile Stress	60.0	MPa	ISO 527-2
Tensile Strain (Break)	10	%	ISO 527-2
Flexural Modulus	2800	MPa	ISO 178
Flexural Stress	90.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
--	6.0	kJ/m²	ISO 179/1eA
-40°C	3.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
--	40	kJ/m²	ISO 179/1eU

-40°C	20	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	70.0	°C	ISO 75-2/A
Vicat Softening Temperature	200	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating (3.0 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	80	°C	
Drying Time - Desiccant Dryer	2.0 - 12	hr	
Suggested Max Moisture	0.15	%	
Processing (Melt) Temp	280 - 300	°C	
Mold Temperature	80 - 120	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

