

Toraycon® 1050M

Polybutylene Terephthalate

Toray Plastics (Malaysia) Sdn. Bhd.

Message:

Toraycon® 1050M is a Polybutylene Terephthalate (PBT) material. It is available in Asia Pacific or Europe. Primary attribute of Toraycon® 1050M: RoHS Compliant.

General Information			
RoHS Compliance		RoHS Compliant	
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.31	g/cm ³	ASTM D792
--	1.32	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/1.0 kg)	47	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	91.0	cm ³ /10min	ISO 1133
Viscosity Number ¹ (0.5% OCP)	74.0	cm ³ /g	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield	55.0	MPa	ASTM D638
--	60.0	MPa	ISO 527-2
Tensile Elongation			
Break	12	%	ASTM D638
Break	16	%	ISO 527-2
Flexural Modulus			
--	2300	MPa	ASTM D790
--	2500	MPa	ISO 178
Flexural Strength			
--	81.0	MPa	ASTM D790
--	87.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	3.0	kJ/m ²	ISO 179
Notched Izod Impact	34	J/m	ASTM D256
Thermal	Nominal Value	Unit	
Melting Temperature	224	°C	
NOTE			

1.

Intrinsic Viscosity under phenol/dichlorobenzen method, 1050M = 0.77 dl/g, 1100M = 0.83dl/g, 1200M = 1.08dl/g.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

