

Karina BLACK PVC COMPOUND TR-55-48/1 1-Y

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

PVC COMPOUND WITH ADDITION OF NITRILE RUBBER RECOMMENDED FOR INJECTION OF PARTS FOR GENERAL PURPOSE.

General Information			
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.20 to 1.26	g/cm ³	ASTM D792
Color a	-0.790 to 0.810		ME 12
Color b	-1.40 to 0.200		ME 12
Color L	25.9 to 27.5		ME 12
Abrasion Resistance	< 265	mm ³	DIN 53516
Tear Resistance	> 25.0	kN/m	DIN 53507
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	53 to 57		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 6.86	MPa	ASTM D638
Tensile Elongation (Yield)	> 300	%	ASTM D638
NOTE			
1.	24 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT