

Kangxi® FRABSMIV-0

Acrylonitrile Butadiene Styrene

Wuxi Kangxi Plastics Technology Co.,Ltd.

Message:

Kangxi®FRABSMIV-0 is an acrylonitrile butadiene styrene (ABS) product. It can be processed by injection molding and is available in the Asia-Pacific region. Kangxi®FRABSMIV-0 application areas include electrical appliances, automobile industry and sporting goods.

Features include:

flame retardant/rated flame

ROHS certification

Flame Retardant

Low shrinkage

high gloss

General Information			
Features	Good dimensional stability		
	Low warpage		
	Highlight		
	High strength		
	Low shrinkage		
	Flame retardancy		
Uses	Electrical appliances		
	Application in Automobile Field		
	Sporting goods		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.17	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.40	%	ASTM D955
Transverse flow	0.60	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	90		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ²	40.0	MPa	ASTM D638
Tensile Elongation ³ (Break)	15	%	ASTM D638
Flexural Modulus ⁴	2150	MPa	ASTM D790
Flexural Strength ⁵	55.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	120	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 6.40mm	90.0	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	80.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.6 mm	V-0		UL 94
3.2 mm	V-0		UL 94
Additional Information	Nominal Value	Unit	Test Method
Weather Resistance - 24 hr (23°C)	0.040	%	ASTM D570
Injection	Nominal Value	Unit	
Drying Temperature	70 - 80	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	180 - 230	°C	
Middle Temperature	180 - 230	°C	
Front Temperature	180 - 230	°C	
Processing (Melt) Temp	200 - 230	°C	
Mold Temperature	30 - 60	°C	
NOTE			
1.	23°C		
2.	50 mm/min		
3.	50 mm/min		
4.	2.0 mm/min		
5.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

