

FERREX® GPP35CS68UL BLACK

Polypropylene

Ferro Corporation

Message:

FERREX® GPP35CS68UL BLACK is a Polypropylene material filled with 36% calcium carbonate. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of FERREX® GPP35CS68UL BLACK are:

High Gloss

Impact Modified

Typical application of FERREX® GPP35CS68UL BLACK: Automotive

General Information			
Filler / Reinforcement	Calcium Carbonate,36% Filler by Weight		
Additive	Impact Modifier		
Features	High Gloss		
	Impact Modified		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.5	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	1.3	%	
Across Flow	1.6	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	19.3	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	80	%	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 23°C	1480	MPa	
Tangent : 23°C	1530	MPa	
Flexural Strength (23°C)	32.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	270	J/m	ASTM D256
Unnotched Izod Impact (23°C)	1300	J/m	ASTM D4812
Gardner Impact (23°C)	31.6	J	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	90.6	°C	
1.8 MPa, Unannealed	54.4	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

