

TYNEP® P8150

Polybutylene Terephthalate + PET

Tyne Plastics LLC.

Message:

TYNEP® P8150 is a Polybutylene Terephthalate + PET (PBT+PET) material filled with 15% glass fiber. It is available in North America. Primary attribute of TYNEP® P8150: High Gloss.

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Features	High Gloss		
Appearance	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Water Absorption (24 hr)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	89.6	MPa	ASTM D638
Tensile Elongation (Yield)	3.0	%	ASTM D638
Flexural Modulus	4480	MPa	ASTM D790
Flexural Strength	131	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	32	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	270	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	160	°C	
1.8 MPa, Unannealed	204	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	6.0E+16	ohms·cm	ASTM D257
Dielectric Strength (1.57 mm, in Air)	24	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.50		ASTM D150
Dissipation Factor (1 MHz)	0.020		ASTM D150

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

