

LONGLITE® LCP LCP-270 B3G

Liquid Crystal Polymer

CCP Group

Message:

LCP-300/ LCP-270 is a high heat-resistance and anisotropic, Type I/ Type II grade Liquid Crystalline Polymer Compound
LCP-300/LCP-270 appears low viscosity and high fluidity while operating temperature is higher than its melting point.

General Information			
UL YellowCard	E59481-101575821	E59481-101572951	
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	General Purpose		
	High Flow		
	Low Viscosity		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.61	g/cm³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	150	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.0	%	ISO 527-2
Flexural Modulus (23°C)	15000	MPa	ISO 178
Flexural Stress (23°C)	220	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	20	kJ/m²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	270	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (2.00 mm)	> 13	kV/mm	ASTM D149
Arc Resistance	150	sec	ASTM D495
Comparative Tracking Index	125	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	140	°C	
Drying Time	4.0	hr	
Rear Temperature	300 to 320	°C	
Middle Temperature	320 to 340	°C	
Front Temperature	340 to 360	°C	

Nozzle Temperature	340 to 360	°C
Mold Temperature	40.0 to 120	°C
Injection Pressure	98.1 to 137	MPa
Holding Pressure	29.4 to 68.6	MPa
Back Pressure	0.800 to 1.00	MPa
Screw Speed	40 to 120	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

