

Durethan® BKV 130 H3.0 DUS008 000000

Polyamide 6

LANXESS GmbH

Message:

PA 6, 30 % glass fibers, injection molding, improved impact strength, heat-aging stabilized

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 30% filler by weight		
Additive		heat stabilizer		
Features		Impact resistance, good		
		Thermal Stability		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.37	--	g/cm ³	ISO 1183
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	9000	5200	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	160	100	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	4.0	7.0	%	ISO 527-2/5
Flexural Modulus ¹ (23°C)	8000	4800	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% strain, 23°C	230	115	MPa	ISO 178/A
23°C ²	250	145	MPa	ISO 178/A
Flexural Strain at Flexural Strength ³ (23°C)	5.0	7.0	%	ISO 178/A
ISO Shortname	PA6-HI, GHR, 14-090, GF30	--		ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	10	10	kJ/m ²	ISO 179/1eA
23°C	18	28	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	80	80	kJ/m ²	ISO 179/1eU
23°C	95	110	kJ/m ²	ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	220	--	°C	ISO 75-2/B

1.8 MPa, not annealed	205	--	°C	ISO 75-2/A
Melting Temperature ⁴	222	--	°C	ISO 11357-3
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	260 - 290		°C	
Mold Temperature	80.0 - 100		°C	
NOTE				
1.	2.0 mm/min			
2.	2.0 mm/min			
3.	2 mm/min			
4.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

