

KOPLA PA66 KDR1021

Polyamide 66

KOPLA Co., Ltd.

Message:

KOPLA PA66 KDR1021 is a Polyamide 66 (Nylon 66) material filled with glass fiber. It is available in Asia Pacific.

Important attributes of KOPLA PA66 KDR1021 are:

Flame Rated

Impact Modified

Typical applications include:

Electrical/Electronic Applications

Automotive

Sporting Goods

General Information	
Filler / Reinforcement	Glass Fiber
Additive	Impact Modifier
Features	Impact Modified
Uses	Automotive Exterior Parts Electrical Parts Electrical/Electronic Applications Sporting Goods

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.40 to 1.0	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.80	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	121		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	123	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	5.0	%	ASTM D638
Flexural Modulus (23°C)	5100	MPa	ASTM D790
Flexural Strength (23°C)	172	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	160	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	250	°C	
1.8 MPa, Unannealed	235	°C	
Melting Temperature	260	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+13 to 1.0E+15	ohms · cm	ASTM D257

Dielectric Strength	25	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

