UmaPET LIMH

Polyethylene Terephthalate

Ester Industries Ltd.

Message:

KEY FEATURES

UmaPET LIMH is high barrier metallized film, metallized on chemical surface other side plain. It exhibits high barrier properties along with superior metal to film bond strength/adhesion.

It has superior mechanical properties, flex crack resistance and excellent gloss.

APPLICATIONS

UmaPET LIMH is used as high barrier layer in flexible packaging applications which require high barrier and high bond strength in laminates.

Typical usage as barrier layer in laminates for confectionary, snacks, instant drink powder, milk powder, juice powder, tea, coffee, shampoo etc.

| General Information | | | |
|------------------------------------------------|-----------------------|----------------------------------------|-----------------|
| Features | Barrier Resin | | |
| | Bondability | | |
| | Good Adhesion | | |
| | Good Crack Resistance | | |
| | High Gloss | | |
| | Metallizable | | |
| | | | |
| Uses | Film | | |
| | Laminates | | |
| | Packaging | | |
| | | | |
| Forms | Film | | |
| Physical | Nominal Value | Unit | Test Method |
| Molding Shrinkage | | | ASTM D1204 |
| Flow: 150°C, 30 min, 0.0120 mm | 2.5 | % | |
| Across Flow: 150°C, 30 min, 0.0120 mm | 0.40 | % | |
| Surface Tension - Metallized side (12.0 μm) | 56 | mN/m | ASTM D2578 |
| Yield (12.0 μm) | 59.5 | m²/kg | Internal Method |
| Optical Density (12.0 µm) | -2.4 to 7.6 | % | Internal Method |
| Films | Nominal Value | Unit | Test Method |
| Film Thickness - Tested | 12 | μm | |
| Film Thickness - Recommended / Available | 12 μm | | |
| Tensile Strength | | | ASTM D882 |
| MD : Break, 12 μm | 206 | MPa | |
| TD : Break, 12 µm | 216 | MPa | |
| Tensile Elongation | | | ASTM D882 |
| MD : Break, 12 µm | 100 | % | |
| TD : Break, 12 µm | 90 | % | |
| Oxygen Permeability ¹ (23°C, 12 µm) | < 0.700 | cm ³ /m ² /24 hr | ASTM D3985 |

| Water Vapor Transmission ² | < 0.40 | g/m²/24 hr | ASTM F1249 |
|---------------------------------------|----------------------|------------|------------|
| NOTE | | | |
| 1. | 0%RH | | |
| 2 | 37.8°C. 90%RH. 12 um | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

