

Aristech Altair® I-300

Acrylic
Aristech Acrylics LLC

Message:

Aristech Acrylics LLC Altair® I-300 is a partially "cross-linked" commercial continuous cast acrylic sheet with unparalleled thermoforming properties. Aristech Acrylics LLC Altair® I-300 was developed for plumbingware, spa, automotive and other applications.

General Information			
UL YellowCard	E87207-252294		
Features	Crosslinkable		
	Good Thermal Stability		
	Low to No Odor		
	Low to No Taste		
Uses	Automotive Applications		
	Plumbing Parts		
	Spas		
Forms	Sheet		
Processing Method	Thermoforming		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.19	g/cm ³	ASTM D792
Water Absorption (Saturation, 3.18 mm)	0.33	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale, 3.18 mm)	90 to 100		ASTM D785
Barcol Hardness (3.18 mm)	48 to 52		ASTM D2583
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (3.18 mm)	3170	MPa	ASTM D638
Tensile Strength (Yield, 3.18 mm)	68.9	MPa	ASTM D638
Tensile Elongation (Break, 3.18 mm)	5.5	%	ASTM D638
Flexural Modulus (3.18 mm)	3100	MPa	ASTM D790
Flexural Strength (3.18 mm)	107	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (3.18 mm)	246	J/m	ASTM D6110
Thermal Stability ² (180°C, 3.18 mm)	No degradation		ASTM D4802
UV Transmittance ³ (250 to 370 nm)	< 1.0	%	
Hot Forming Temperature (3.18 mm)	171 to 193	°C	Internal Method
Notched Izod Impact (3.18 mm)	21	J/m	ASTM D256A
Instrumented Dart Impact ⁴ (3.18 mm)	4.07	J	Internal Method
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.18 mm)	87.8	°C	ASTM D648
CLTE - Flow (3.18 mm)	7.4E-5	cm/cm/°C	ASTM D696
Specific Heat ⁵	1460	J/kg/°C	ASTM C351
Thermal Conductivity ⁶	0.20	W/m/K	Internal Method
Optical	Nominal Value	Unit	Test Method
Refractive Index ⁷	1.490		ASTM D542
Transmittance			ASTM D1003
3180 μm ⁸	93.0	%	
3180 μm ⁹	93.0	%	
Haze			ASTM D1003
3180 μm ¹⁰	1.0	%	
3180 μm ¹¹	0.80	%	
Yellowness Index ¹² (3.18 mm)	0.45	YI	ASTM D1925

NOTE

- 0.125 in
- 30 min
- UV Spectrophotometer
- FTMS 406-M-1074
- 0.125 in
- 0.125 in
- 0.125 in, Unaged
- Aged
- Unaged
- Aged
- Unaged
- Aged

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT