

SKYBON EW-100Q

Polyester Adhesive
SK Chemicals

Message:
Thermoplastic Copolyester for waterborne applications

General Information			
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Acid Number	< 5.00	mg KOH/g	Internal Method
Intrinsic Viscosity - o-Chlorophenol at 35°C	0.42	dl/g	Internal Method
OH Value	10.0 to 15.0	mg KOH/g	Internal Method
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	44.0	°C	DSC

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT