

Crastin® S600F20 BK851

THERMOPLASTIC POLYESTER RESIN

DuPont Performance Polymers

Message:

Unreinforced Medium Viscosity Polybutylene Terephthalate

General Information			
UL YellowCard	E41938-257808		
Agency Ratings	UL Unspecified Rating		
Processing Method	Injection Molding		
Part Marking Code (ISO 11469)	>PBT<		
Resin ID (ISO 1043)	PBT		
Physical	Nominal Value	Unit	Test Method
Density	1.31	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	18	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.7	%	
Flow	1.7	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2500	MPa	ISO 527-2
Tensile Stress (Yield)	57.0	MPa	ISO 527-2
Tensile Strain (Yield)	6.0	%	ISO 527-2
Nominal Tensile Strain at Break	40	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.5	kJ/m ²	ISO 179/1eA
Notched Izod Impact Strength (23°C)	4.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Melting Temperature ¹	224	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Burning Rate (1.00 mm)	24	mm/min	ISO 3795
Flammability Classification (1.50 mm)	HB		IEC 60695-11-10, -20
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

