

Edgetek™ PK-30GF/000 FCR NC

Polyetheretherketone

PolyOne Corporation

Message:

30 % Glass Fiber Reinforced PEEK Compound with Ultra High Flowability

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Appearance	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.48	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (400°C/2.16 kg)	11	g/10 min	ISO 1133
Molding Shrinkage (3.00 mm)	0.20 - 0.50	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	190	MPa	ASTM D638
Tensile Elongation (Break)	3.0 - 4.0	%	ASTM D638
Flexural Modulus ²	11000	MPa	ASTM D790
Flexural Strength ³	290	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	100	J/m	ASTM D256
Unnotched Izod Impact (23°C, 3.20 mm)	950	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	320	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-0		Internal method
Injection	Nominal Value	Unit	
Drying Temperature	150 - 160	°C	
Drying Time	4.0 - 6.0	hr	
Rear Temperature	350 - 390	°C	
Middle Temperature	350 - 390	°C	
Front Temperature	350 - 390	°C	
Mold Temperature	170 - 190	°C	
Injection instructions			
Injection Pressure: MED-HIGHHold Pressure: MED-HIGHScrew Speed: MODERATEBack Pressure: LOW			
NOTE			

1.	5.0 mm/min
2.	1.3 mm/min
3.	1.3 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

