

APEX® RE 9203

Rigid Polyvinyl Chloride

Teknor Apex Company

Message:

APEX® RE 9203 is a Rigid Polyvinyl Chloride material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

General Information			
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.44	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 10 sec)	82		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹ (Compression Molded)	2650	MPa	ASTM D638
Tensile Strength ² (Break, Compression Molded)	44.8	MPa	ASTM D638
Tensile Elongation (Break)	60	%	ASTM D638
Flexural Modulus (Compression Molded)	2690	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm, Compression Molded)	170	J/m	ASTM D256
Drop Impact Resistance ³ (23°C)	93.4	J/cm	ASTM D4226
NOTE			
1.	5.1 mm/min		
2.	5.1 mm/min		
3.	Procedure A, TUP		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT