

ATTANE™ 4607GC

Ultra Low Density Polyethylene Resin

The Dow Chemical Company

Message:

ATTANE™ 4607GC Ultra Low Density Ethylene/Hexene Copolymer is a skin layer in cast film offers excellent low temperature hot tack properties combined with outstanding tear and impact strength. In stretch film applications, ATTANE™ 4607GC Ultra Low Density Ethylene/Hexene Copolymer exhibits excellent stretchability as well as good physical and cling properties. ATTANE™ 4607GC Ultra Low Density Ethylene/Hexene Copolymer can also be utilised in blown film coextrusion where it is combined with other resins having excellent bubble stability allowing ATTANE™ 4607GC Ultra Low Density Ethylene/Hexene Copolymer to be used as a sealant in multilayer film structures.

Applications:

Cling layer in cast stretch film.

Sealants in cast and blown films.

Complies with:

EU, No 10/2011- U.S. FDA FCN 741

Consult the regulations for complete details

General Information			
Agency Ratings	FDA FCN 741		
	Europe No 10/2011		
Forms	Particle		
Processing Method	cast film		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.904	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.0	g/10 min	ISO 1133
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	23	µm	
Film Puncture Energy (23 µm)	5.00	J	Internal method
Film Puncture Force (23 µm)	48.0	N	Internal method
Tensile Stress			ISO 527-3
MD: Yield, 23 µm	4.30	MPa	ISO 527-3
TD: Yield, 23 µm	3.60	MPa	ISO 527-3
MD: Break, 23 µm	33.0	MPa	ISO 527-3
TD: Break, 23 µm	23.0	MPa	ISO 527-3
Tensile Elongation			ISO 527-3
MD: Break, 23 µm	500	%	ISO 527-3
TD: Break, 23 µm	630	%	ISO 527-3
Dart Drop Impact (23 µm)	180	g	ISO 7765-1/A
Elmendorf Tear Strength			ASTM D1922
MD : 23 µm	190	g	ASTM D1922
TD : 23 µm	390	g	ASTM D1922
Unstretched bond	130	g	ASTM D4649
Thermal	Nominal Value	Unit	Test Method

Vicat Softening Temperature	72.0	°C	ASTM D1525
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 23.0 μm)	92		ASTM D2457
Haze (23.0 μm)	0.70	%	ASTM D1003

Additional Information

对于在 Lab Collin 生产线上采用 15 米/分冷却辊于 25°C 下生产的单层薄膜所测量的薄膜属性.

Extrusion	Nominal Value	Unit
Melt Temperature	190 - 260	°C

Extrusion instructions

铸造薄膜挤出的制造条件:

熔体温度:190 - 260 °C

建议的厚度范围:10 - 60 μm

脱离速度:150 - 300 米/分

冷却辊温度:20 - 60 °C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

