

SANTAC® UT-61

Acrylonitrile Butadiene Styrene

Nippon A&L; Inc.

Message:

SANTAC®UT-61 is an acrylonitrile butadiene styrene (ABS) material. This product is available in North America or Asia Pacific region. The processing method is injection molding. SANTAC®The main characteristics of the UT-61 are: flame retardant/rated flame.

General Information			
UL YellowCard	E54706-245133		
Agency Ratings	JHOSPA not rated		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.05	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	35.0	cm ³ /10min	ISO 1133
Molding Shrinkage	0.40 - 0.60	%	Internal method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	116		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	50.0	MPa	ISO 527-2
Flexural Modulus (23°C)	2400	MPa	ISO 178
Flexural Stress (23°C)	76.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	15	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	81.0	°C	ISO 75-2/A
CLTE - Flow (23 to 80°C)	8.0E-5	cm/cm/°C	JIS K7197
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Additional Information			
Ball Pressure Registration Temperature: 90°C			
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 90.0	°C	
Drying Time	> 3.0	hr	
Rear Temperature	200 - 260	°C	
Middle Temperature	200 - 260	°C	
Front Temperature	200 - 260	°C	
Mold Temperature	40.0 - 80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

