

Hylex® P1017L

Polycarbonate

Ravago Manufacturing Americas, LLC

Message:

Polycarbonate, High Flow

General Information			
Features	High Flow		
RoHS Compliance	RoHS Compliant		
UL File Number	E157012		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	17	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.50 to 0.70	%	ISO 294-4
Water Absorption (24 hr)	0.15	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	80		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	70.0	MPa	ISO 527-2
Tensile Strain (Break)	120	%	ISO 527-2
Flexural Modulus	2380	MPa	ISO 178
Flexural Stress	93.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	54	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	140	°C	ISO 75-2/B
1.8 MPa, Unannealed	129	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	4.0E+16	ohms · cm	ASTM D257
Dielectric Strength	16	kV/mm	ASTM D149
Arc Resistance	120	sec	ASTM D495

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

