NOVAPOL® TF-0219-E

Linear Low Density Polyethylene

NOVA Chemicals

Message:

 $NOVAPOL @ \ TF-0219-E \ is \ a \ Linear \ Low \ Density \ Polyethylene \ material. \ It \ is \ available \ in \ North \ America \ for \ film \ extrusion.$

Important attributes of NOVAPOL® TF-0219-E are:

Antioxidant

Food Contact Acceptable

Good Toughness

Hexene Comonomer

Typical applications include:

Film

Food Contact Applications

Wrap

General Information			
Additive	Antioxidant		
Features	Antioxidant		
	Food Contact Acceptable		
	Good Toughness		
	Hexene Comonomer		
	Low Density		
	Low Gel		
Uses	Cast Film		
	Stretch Wrap		
Among Potings	FDA 21 CFD 177 1F20(a) 2.1a		
Agency Ratings	FDA 21 CFR 177.1520(c) 3.1a		
Forms	Pellets		
Processing Method	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.918	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	20	μm	
Secant Modulus			ASTM D882
1% Secant, MD : 20 μm, Cast Film	150	MPa	
1% Secant, TD : 20 μm, Cast Film	170	MPa	
Tensile Strength			ASTM D882
MD : Yield,20 μm, Cast Film	10.0	MPa	
TD : Yield,20 µm, Cast Film	10.0	MPa	
MD : Break, 20 µm,Cast Film	39.0	MPa	

TD : Break, 20 µm,Cast Film	29.0	MPa	
Tensile Elongation			ASTM D882
MD : Break, 20 μm,Cast Film	500	%	
TD : Break, 20 µm,Cast Film	780	%	
Dart Drop Impact (20 μm, Cast Film)	100	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 20 μm, Cast Film	260	g	
TD : 20 μm, Cast Film	420	g	
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 20.0 μm, Cast Film)	90		ASTM D2457
Haze (20.0 μm, Cast Film)	2.0	%	ASTM D1003
Additional Information	Nominal Value	Unit	Test Method
Low Friction Puncture - Cast Film (20.0 µm)	500	J/cm	Internal Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

