

NYCOA Polyamide 7550 Nat

Polyamide 12

Nycoa (Nylon Corporation of America)

Message:

NYCOA 7550 Nat is a heat stabilized Nylon 12 alloy that offers outstanding toughness, increased flexibility, and impact strength. It has been specially formulated to give excellent resistance to zinc chloride and other automotive fluids. The material offers high resistance to moisture absorption. NYCOA 7550 Nat is suitable for extrusion of highly flexible tubing. It exhibits outstanding processability, chemical resistance, good heat stability and an excellent balance of mechanical properties. This grade is available with custom additive packages: UV stabilizer, flame retardant and/or custom colors. Typical applications include high performance automotive tubing; air brakes, fuel lines and lube lines and profile extrusion.

General Information	
Additive	heat stabilizer
Features	Low hygroscopicity
	Impact resistance, good
	Workability, good
	Good flexibility
	Good chemical resistance
	Thermal Stability
	Good toughness
Uses	Pipe fittings
	Application in Automobile Field
	Fuel line
	Profile
Appearance	Available colors
	Natural color
Forms	Particle
Processing Method	Extrusion
	Profile extrusion molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.01	g/cm ³	ASTM D792
Water Absorption			ASTM D570
24 hr	0.34	%	ASTM D570
Saturation	1.0	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	35.0	MPa	ASTM D638
Tensile Elongation ² (Break)	500	%	ASTM D638
Flexural Modulus ³	200	MPa	ASTM D790

Flexural Strength ⁴	8.96	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
	No fracture		
Notched Izod Impact (6.35 mm)	750 J/m		ASTM D256
Thermal	Nominal Value	Unit	
Melting Temperature	174 - 206	°C	
Additional Information			
The value listed as Melting Point, was tested in accordance with ASTM D789.Tensile Elongation at Break, ASTM D638, 2 in/min: 500+%			
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

