

Lusep® SP2306F

Syndiotactic Polystyrene

LG Chem Ltd.

Message:

Description

Flame Retardant

Application

Pump Units, Pick-up Lends Holder, etc.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Flame Retardant		
Uses	Pump Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.40	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.30 to 0.90	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break, 3.20 mm)	113	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	2.0	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	9320	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 3.20 mm)	186	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.40 mm ⁵	260	°C	
0.45 MPa, Unannealed, 6.40 mm ⁶	230	°C	
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (23°C, 1.00 mm)	31	kV/mm	ASTM D149
Comparative Tracking Index (Solution A)	400 to 600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 100	°C	
Drying Time	3.0 to 5.0	hr	
Suggested Max Moisture	< 0.020	%	
Rear Temperature	270 to 290	°C	
Middle Temperature	280 to 310	°C	
Front Temperature	290 to 310	°C	
Nozzle Temperature	280 to 310	°C	

Processing (Melt) Temp	280 to 310	°C
Mold Temperature	80.0 to 150	°C
Screw Speed	40 to 80	rpm

NOTE

1.	5.0 mm/min
2.	5.0 mm/min
3.	1.3 mm/min
4.	1.3 mm/min
5.	4.6kg
6.	18.6kg

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

