

INELEC PPCF20

Polypropylene
Infinity LTL Engineered Compounds

Message:
20% CARBON FIBER REINFORCED, ELECTRICALLY CONDUCTIVE POLYPROPYLENE

General Information			
Filler / Reinforcement	Carbon Fiber,20% Filler by Weight		
Features	Electrically Conductive		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.998	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.10 to 0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	46.9	MPa	ASTM D638
Flexural Modulus	6890	MPa	ASTM D790
Flexural Strength	65.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	53	J/m	ASTM D256
Unnotched Izod Impact	130	J/m	ASTM D4812
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 to 1.0E+6	ohms	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	76.7	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	193 to 227	°C	
Mold Temperature	37.8	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	40 to 70	rpm	
Vent Depth	0.013 to 0.025	mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT