

Santoprene™ 101-55W255

Thermoplastic Vulcanizate

ExxonMobil Chemical

Message:

It is a soft, black thermoplastic vulcanized elastomer (TPV) in the thermoplastic elastomer (TPE) series. This material is designed for use in household washing machines and dishwashers and contains a stable system to prevent catalytic degradation of copper and other metals. This brand of Sanduping TPV is a shear rate dependent product that can be processed on conventional thermoplastic injection molding or extrusion molding equipment. This is a polyolefin-based material that can be recycled in the production process.

General Information	
UL YellowCard	E80017-564849
Features	Low compressive deformability
	Recyclable materials
	Ozone resistance
	Copper contact stability
Uses	Washer
	Home appliance components
	Seals
Agency Ratings	UL QMFZ2
	UL QMFZ8
RoHS Compliance	RoHS compliance
UL File Number	E80017
Appearance	Black
Forms	Particle
Processing Method	Multiple injection molding
	Co-extrusion molding
	Extrusion
	Sheet extrusion molding
	Profile extrusion molding
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	0.968	g/cm ³	ASTM D792
--	0.970	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shaw A, 15 seconds, 23°C, 2.00mm)	61		ISO 868

Elastomers	Nominal Value	Unit	Test Method
Tensile Stress - Across Flow (100% Strain, 23°C)	1.80	MPa	ASTM D412, ISO 37
Tensile Strength - Across Flow (Break, 23°C)	5.20	MPa	ASTM D412, ISO 37
Tensile Elongation - Across Flow (Break, 23°C)	510	%	ASTM D412, ISO 37
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.50 mm	HB		UL 94
3.00 mm	HB		UL 94
Additional Information			
如果适用,这是基于扇形浇口注塑成型的平板测试结果.拉伸强度,伸长率和拉伸应力沿垂直流动方向测定 - ISO 1 型,ASTM die C.从埃克森美孚欧洲分支机构直接购买的所有产品都符合 REACH 法规. 对于埃克森 美孚未进口至欧洲的产品,用户应自行评估其是否满足 REACH 法规.			
Legal statement			
未经埃克森美孚化工书面允许,这种产品包括其产品名称,不得在任何医疗应用领域予以使用或有关详细的产品监管信息,请联系客户服务.			
Injection instructions			
Santoprene TPV与乙缩醛和PVC不相容.更多关于加工和模具设计的信息,请查阅我们的《注射成型指南》.			
Extrusion instructions			
Santoprene TPV与乙缩醛和PVC不相容.更多关于加工和模具设计的信息,请查阅我们的《挤出成型指南》.			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

