

ALFATER XL® A80I 4FC0000

Thermoplastic Vulcanizate

ALBIS PLASTIC GmbH

Message:

ALFATER XL® A80I 4FC0000 is a Thermoplastic Vulcanizate (TPV) product. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America. Applications of ALFATER XL® A80I 4FC0000 include food contact applications, handles, hose/tubing and sealing applications.

Characteristics include:

REACH Compliant

RoHS Compliant

General Information			
Features	Alkali Resistant		
	Ozone Resistant		
Uses	Handles		
	Non-specific Food Applications		
	Seals		
	Tubing		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.940	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	80		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	3.50	MPa	ISO 527-2
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (Break)	8.10	MPa	ISO 37
Tensile Elongation (Break)	560	%	ISO 37
Tear Strength	35	kN/m	ISO 34-1
Compression Set (100°C, 22 hr)	53	%	ISO 815
Thermal	Nominal Value	Unit	
Service Temperature	-40 to 125	°C	
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	70.0 to 80.0	°C	
Drying Time - Desiccant Dryer	2.0 to 4.0	hr	
Processing (Melt) Temp	195 to 215	°C	
Mold Temperature	10.0 to 70.0	°C	
Injection Rate	Fast		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

