

UBE Nylon 1022B

Polyamide 6

UBE Engineering Plastics, S.A.

Message:

UBE Nylon 1022B is a Polyamide 6 (Nylon 6) product. It can be processed by extrusion or injection molding and is available in North America. Typical application: Fabrics/Fibers.
Characteristics include:
Flame Rated
Chemical Resistant
Good Mold Release
Heat Resistant
Impact Resistant

General Information				
UL YellowCard		E173981-100115867	E48133-240254	
Features		Good Abrasion Resistance		
		Good Chemical Resistance		
		Good Impact Resistance		
		Good Mold Release		
		High Heat Resistance		
		High Rigidity		
		Medium Viscosity		
		Oil Resistant		
		Self Lubricating		
		Solvent Resistant		
		Sound Damping		
		Vibration Damping		
Uses		Monofilaments		
Forms		Pellets		
Processing Method		Extrusion		
		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.14	--	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.4 to 1.5	--	%	ASTM D955
Water Absorption				ASTM D570
24 hr	1.8	--	%	
Saturation	11	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ASTM D785
M-Scale	85	55		

R-Scale	120	85		
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength				ASTM D638
Yield	73.5	39.2	MPa	
Break	70.5	--	MPa	
Tensile Elongation				ASTM D638
Yield	8.0	--	%	
Break	200	200	%	
Flexural Modulus	2450	686	MPa	ASTM D790
Flexural Strength (Yield)	108	39.2	MPa	ASTM D790
Compressive Strength	19.6	9.80	MPa	ASTM D695
Shear Strength	63.7	58.8	MPa	ASTM D732
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact				ASTM D256
-30°C	49	--	J/m	
23°C	69	490	J/m	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
0.45 MPa, Unannealed	170	--	°C	
1.8 MPa, Unannealed	65.0	--	°C	
Melting Temperature	215 to 225	--	°C	
CLTE - Flow	8.0E-5	--	cm/cm/°C	ASTM D696
RTI Elec (3.05 mm)	65.0	--	°C	UL 746
RTI Imp (3.05 mm)	65.0	--	°C	UL 746
RTI Str (3.05 mm)	65.0	--	°C	UL 746
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+15	1.0E+12	ohms·cm	ASTM D257
Dielectric Strength	20	--	kV/mm	ASTM D149
Dielectric Constant				ASTM D150
60 Hz	3.90	9.00		
1 MHz	3.50	4.50		
Dissipation Factor				ASTM D150
60 Hz	0.010	0.10		
1 MHz	0.020	0.12		
Arc Resistance (3.05 mm)	118	--	sec	ASTM D495
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (3.05 mm)	V-2	--		UL 94
Injection	Dry	Unit		
Suggested Max Moisture	0.10		%	
Rear Temperature	220		°C	
Middle Temperature	230		°C	

Front Temperature	245	°C
Nozzle Temperature	245	°C
Processing (Melt) Temp	250	°C
Mold Temperature	70.0 to 80.0	°C
Injection Pressure	63.7	MPa
Back Pressure	9.80	MPa
Screw Speed	100 to 150	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

