

ULTEM™ CRS5201R resin

Polyether Imide

SABIC Innovative Plastics

Message:

20% Glass fiber filled, standard flow Polyetherimide copolymer (Tg 225C) with internal mold release and enhanced chemical resistance to strong acids, bases, aromatics, and ketones. ECO Conforming.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
Additive	demoulding		
Features	Comply with ECO		
	Copolymer		
	Good chemical resistance		
	alkali resistance		
	acid resistance		
Agency Ratings	EU Eco		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (337°C/6.6 kg)	3.1	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	6890	MPa	ASTM D638
Tensile Strength ² (Break)	131	MPa	ASTM D638
Tensile Elongation ³ (Break)	5.0	%	ASTM D638
Flexural Modulus ⁴ (100 mm Span)	6890	MPa	ASTM D790
Flexural Strength ⁵ (Yield, 100 mm Span)	214	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	75	J/m	ASTM D256
Reverse Notch Izod Impact (3.20 mm)	480	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	218	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	149	°C	
Drying Time	4.0 - 6.0	hr	
Drying Time, Maximum	24	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	
Rear Temperature	343 - 366	°C	
Middle Temperature	354 - 377	°C	

Front Temperature	366 - 388	°C
Nozzle Temperature	360 - 382	°C
Processing (Melt) Temp	366 - 388	°C
Mold Temperature	135 - 163	°C
Back Pressure	0.345 - 0.689	MPa
Screw Speed	40 - 70	rpm
Vent Depth	0.025 - 0.076	mm

NOTE

- | | |
|----|--------------------|
| 1. | 5.0 mm/min |
| 2. | Type 1, 5.0 mm/min |
| 3. | Type 1, 5.0 mm/min |
| 4. | 2.6 mm/min |
| 5. | 2.6 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

