

EcoFast™ FRPC/ABS-50%

Polycarbonate + ABS

LTL Color Compounders, Inc.

Message:

Flame Retardant PC/ABS 50% Recycled Content

Color# 1-17-7

General Information			
UL YellowCard	E178307-635269		
Additive	Flame Retardant		
Recycled Content	Yes,50%		
Features	Flame Retardant		
	Renewable Resource Content		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/2.16 kg)	17	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.40 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	56.5	MPa	
Break	51.7	MPa	
Tensile Elongation			ASTM D638
Yield	5.0	%	
Break	50	%	
Flexural Modulus	2520	MPa	ASTM D790
Flexural Strength	88.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	530	J/m	ASTM D256
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

