

LEXAN™ XHT1141 resin

Polycarbonate

SABIC Innovative Plastics

Message:

XHT1141 is a high flow, high heat polycarbonate copolymer. It is available in a range of opaque and limited transparent colors.

General Information			
Features	Copolymer		
	High liquidity		
	Heat resistance, high		
RoHS Compliance	RoHS compliance		
Appearance	Opacity		
	Available colors		
	Clear/transparent		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR)			ISO 1133
300°C/1.2 kg	16.0	cm ³ /10min	ISO 1133
330°C/2.16 kg	70.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.60 - 0.90	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.30	%	ISO 62
Equilibrium, 23°C, 50% RH	0.30	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2400	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	65.0	MPa	ISO 527-2/50
Fracture	60.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	6.5	%	ISO 527-2/50
Fracture	80	%	ISO 527-2/50
Flexural Modulus ¹	2400	MPa	ISO 178
Flexural Stress	100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ²			ISO 179/1eA
-30°C	12	kJ/m ²	ISO 179/1eA
23°C	16	kJ/m ²	ISO 179/1eA

Charpy Unnotched Impact Strength ³			ISO 179/1eU
-30°C	No Break		ISO 179/1eU
23°C	No Break		ISO 179/1eU
Notched Izod Impact ⁴			ISO 180/1A
-30°C	10	kJ/m ²	ISO 180/1A
23°C	14	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ⁵			ISO 180/1U
-30°C	No Break		ISO 180/1U
23°C	No Break		ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁶			
0.45 MPa, unannealed, 64.0mm span	144	°C	ISO 75-2/Bf
1.8 MPa, unannealed, 64.0mm span	132	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	150	°C	ISO 306/B50
--	152	°C	ISO 306/B120
Linear thermal expansion coefficient			ISO 11359-2
Flow: -40 to 40°C	7.0E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	7.0E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	125	°C	
Drying Time	4.0 - 6.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	
Rear Temperature	270 - 305	°C	
Middle Temperature	280 - 325	°C	
Front Temperature	290 - 335	°C	
Nozzle Temperature	285 - 330	°C	
Processing (Melt) Temp	290 - 335	°C	
Mold Temperature	85.0 - 130	°C	
Back Pressure	0.300 - 0.700	MPa	
Screw Speed	40 - 90	rpm	
Vent Depth	0.025 - 0.080	mm	
NOTE			
1.	2.0 mm/min		
2.	80*10*3 sp=62mm		
3.	80*10*3 sp=62mm		
4.	80*10*3		
5.	80*10*3		
6.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

