

ALTECH® PA66 A 2030/516 GF30 IM

Polyamide 66
ALBIS PLASTIC GmbH

Message:

ALTECH® PA66 A 2030/516 GF30 IM is a Polyamide 66 (Nylon 66) product filled with 30% glass fiber. It is available in Asia Pacific, Europe, or North America.

Characteristics include:

REACH Compliant
RoHS Compliant
Heat Stabilizer
High Gloss
Impact Modified

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Heat Stabilizer		
	Impact Modifier		
Features	Heat Stabilized		
	High Gloss		
	Impact Modified		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.32	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8250	MPa	ISO 527-2
Tensile Stress (Break)	140	MPa	ISO 527-2
Tensile Strain (Break)	3.6	%	ISO 527-2
Flexural Modulus	7650	MPa	ISO 178
Flexural Stress	215	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	16	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	95	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	248	°C	ISO 75-2/A
Vicat Softening Temperature	252	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	80.0	°C	
Drying Time - Desiccant Dryer	2.0 to 12	hr	
Suggested Max Moisture	0.15	%	

Processing (Melt) Temp	280 to 300	°C
Mold Temperature	80.0 to 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

