LNP™ THERMOCOMP™ IF006L compound

Polyamide 612

SABIC Innovative Plastics

Message:

LNP THERMOCOMP IF006L is a compound based on Nylon 6/12 resin containing 30% Glass Fiber. Added features of this material include: Low Extractible. Also known as: LNP* THERMOCOMP* Compound IF-1006 LE

Product reorder name: IF006L

General Information			
UL YellowCard	E121562-101343416		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Low Extractables		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	8760	MPa	ASTM D638
Tensile Strength (Break)	135	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	7790	MPa	ASTM D790
Flexural Strength	207	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	85	J/m	ASTM D256
Unnotched Izod Impact (23°C)	590	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	199	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.12 to 0.20	%	
Rear Temperature	254 to 266	°C	
Middle Temperature	260 to 271	°C	
Front Temperature	271 to 282	°C	
Processing (Melt) Temp	271 to 277	°C	
Mold Temperature	65.6 to 93.3	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

