

CALIBRE™ MEGARAD™ 2080-15

Polycarbonate Resin

Trinseo

Message:

CALIBRE™ MEGARAD™ 2080-15 Polycarbonate resin provides end-users of radiation sterilized medical devices a color closer to the water-clear look of the natural resin. When exposed to high energy radiation (gamma or electron beam), CALIBRE MEGARAD 2080-15 resin can reduce the color shift by 50% compared to general purpose polycarbonate resins. CALIBRE 2080-15 resin has undergone biocompatibility testing based on ISO 10993 (Biological Evaluation of Medical Devices) and is suitable for use in approved medical applications.

Main Characteristics:

Stabilized for higher energy radiation

Tested under ISO 10993

Transparent

Contains no mold release

Applications:

Medical applications

General Information			
Additive	Gamma stabilizer		
Features	Electron beam disinfection		
	Radiation disinfection		
	Definition, high		
	Biocompatibility		
Uses	Medical/nursing supplies		
Agency Ratings	ISO 10993		
Appearance	Clear/transparent		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792, ISO 1183/A
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	15	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow	0.50 - 0.70	%	ASTM D955
Flow	0.50 - 0.70	%	ISO 294-4
Water Absorption			ASTM D570, ISO 62
23°C, 24 hr	0.15	%	ASTM D570, ISO 62
Equilibrium, 23°C, 50% RH	0.32	%	ASTM D570, ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2210	MPa	ASTM D638
--	2300	MPa	ISO 527-2/50

Tensile Strength			
Yield ²	62.1	MPa	ASTM D638
Yield	62.0	MPa	ISO 527-2/50
Fracture ³	68.3	MPa	ASTM D638
Fracture	68.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	6.0	%	ASTM D638
Yield	6.0	%	ISO 527-2/50
Fracture ⁵	150	%	ASTM D638
Fracture	150	%	ISO 527-2/50
Flexural Modulus			
-- ⁶	2410	MPa	ASTM D790
--	2400	MPa	ISO 178
Flexural Strength			
-- ⁷	96.5	MPa	ASTM D790
--	98.0	MPa	ISO 178
Taber Abrasion Resistance	45	%	ASTM D1044
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	25	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C	750	J/m	ASTM D256
23°C	75	kJ/m ²	ISO 180/A
Unnotched Izod Impact (23°C)	No Break		ASTM D256, ISO 180
Instrumented Dart Impact ⁸ (23°C, Total Energy)	81.3	J	ASTM D3763
Tensile Impact Strength	378	kJ/m ²	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, annealed	139	°C	ASTM D648
1.8 MPa, not annealed	122	°C	ASTM D648
1.8 MPa, not annealed	120	°C	ISO 75-2/A
1.8 MPa, annealed	136	°C	ASTM D648
Vicat Softening Temperature			
--	148	°C	ASTM D1525 ⁹
--	143	°C	ISO 306/B50
CLTE - Flow (-40 to 82°C)	6.8E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.0E+17	ohms · cm	ASTM D257
Dielectric Strength	17	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
60 Hz	3.00		ASTM D150
1 MHz	3.00		ASTM D150

Dissipation Factor			ASTM D150
50 Hz	1.0E-3		ASTM D150
1 MHz	2.0E-3		ASTM D150
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.586		ASTM D542, ISO 489
Transmittance	89.0	%	ASTM D1003
Haze	1.0	%	ASTM D1003
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	50 mm/min		
5.	50 mm/min		
6.	Method I (three-point load), 2.0 mm/min		
7.	Method I (three-point load), 2.0 mm/min		
8.	3.39 m/sec		
9.	速率 A (50°C/h), 载荷2 (50N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

