

Staramide PF006ES

Polyamide 6

Eurostar Engineering Plastics

Message:

Staramide PF006ES is a 30 % Glass Fiber Reinforced Polyamide 6 Injection Molding Resin

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.37	g/cm ³	ISO 1183
Molding Shrinkage - Flow ¹	0.20 to 0.40	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8500	MPa	ISO 527-2/1
Tensile Stress (Break)	165	MPa	ISO 527-2/5
Tensile Strain (Break)	5.0	%	ISO 527-2/5
Flexural Modulus ²	8200	MPa	ISO 178
Flexural Stress	225	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ³ (23°C)	16	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ⁴ (23°C)	85	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁵ (1.8 MPa, Unannealed, 64.0 mm Span)	215	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 85.0	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	230 to 240	°C	
Middle Temperature	240 to 250	°C	
Front Temperature	240 to 270	°C	
Processing (Melt) Temp	240 to 270	°C	
Mold Temperature	60.0 to 80.0	°C	
NOTE			
1.	Tensile Bar		
2.	2.0 mm/min		
3.	80*10*4		
4.	80*10*4		
5.	80*10*4		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

