

LUVOCOM® 19-8373

Polyamide 46

Lehmann & Voss & Co.

Message:

LUVOCOM® 19-8373 is a polyamide 46 (nylon 46) material containing a carbon fiber reinforced material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

LUVOCOM® The main features of 19-8373 are:

Antistatic

Good stiffness

Wear-resistant

Lubrication

Typical application areas include:

engineering/industrial accessories

Electrical/electronic applications

textile/fiber

Automotive Industry

business/office supplies

| General Information | | | |
|--------------------------------|----------------------------------|-------------------|-------------|
| Filler / Reinforcement | Carbon fiber reinforced material | | |
| Additive | Antistatic property | | |
| | Lubricant | | |
| Features | Low friction coefficient | | |
| | Rigid, good | | |
| | Antistatic property | | |
| | Good strength | | |
| | Good wear resistance | | |
| | Lubrication | | |
| Uses | Gear | | |
| | Textile applications | | |
| | Engineering accessories | | |
| | Switch | | |
| | Application in Automobile Field | | |
| | Business equipment | | |
| Appearance | Bearing | | |
| | Black | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.42 | g/cm ³ | ISO 1183 |
| Molding Shrinkage | 0.20 - 0.50 | % | DIN 16901 |
| Water Absorption (23°C, 24 hr) | < 1.0 | % | |
| Mechanical | Nominal Value | Unit | Test Method |

| | | | |
|--|---------------|-------------------|-------------|
| Tensile Modulus | 17000 | MPa | ISO 527-2 |
| Tensile Stress (Break) | 115 | MPa | ISO 527-2 |
| Tensile Strain (Yield) | 1.2 | % | ISO 527-2 |
| Flexural Modulus | 16000 | MPa | ISO 178 |
| Flexural Stress | 155 | MPa | ISO 178 |
| Flexural Strain at Flexural Strength | 1.4 | % | ISO 178 |
| Maximum operating temperature-Short Term | 160 | °C | |
| Insulation Resistance | > 1.0E+7 | ohms | IEC 60167 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Unnotched Impact Strength (23°C) | 17 | kJ/m ² | ISO 179/1eU |
| Thermal | Nominal Value | Unit | Test Method |
| Continuous Use Temperature | 150 | °C | UL 746B |
| Injection | Nominal Value | Unit | |
| Drying Temperature | | | |
| A | 80.0 | °C | |
| Vacuum dryer, B | 80.0 | °C | |
| Drying Time | | | |
| A | 2.0 - 8.0 | hr | |
| Vacuum dryer, B | 2.0 - 12 | hr | |
| Suggested Max Moisture | 0.10 | % | |
| Rear Temperature | 285 - 315 | °C | |
| Middle Temperature | 305 - 315 | °C | |
| Front Temperature | 305 - 315 | °C | |
| Nozzle Temperature | 280 - 330 | °C | |
| Processing (Melt) Temp | 310 | °C | |
| Mold Temperature | 120 - 140 | °C | |
| Injection instructions | | | |

General

In general LUVOCOM® can be processed on conventional injection moulding machines while observing the usual technical guidelines.

Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials.

Lengthy dwell times for the melts in the cylinder should be avoided.

Lower the temperatures during interruptions!

Predrying (optional)

It is advisable to predry the granulate with a suitable dryer immediately before processing.

The granulate may absorb moisture from the air.

Delivery Form & Storage

Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.

Preferably storage should be effected in dry and normally temperatured rooms

Additional Information

During processing the moisture level should not exceed 0.1%, otherwise molecular degradation and surface defects (e.g. smearing) may occur. As the material absorbs water very rapidly, originally sealed containers should only be opened immediately before processing. Excessively high predrying temperatures may cause discoloration.

The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.

Please contact us for further information.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

