

# Hy-Vin® XQ76054

Rigid Polyvinyl Chloride

INEOS Compounds

## Message:

Rigid PVC Injection Moulding Compound

Colour : Clears and Colours

Application: Easy flow rigid Medical mouldings

Specification : Meets Heavy metal requirements of BS2463, Freedom from toxicity tests & is expected to comply with US Pharmacopoeia biological tests for plastics

General Information			
Features	Good Flow		
Uses	Medical/Healthcare Applications		
Agency Ratings	BS 2463		
Appearance	Clear/Transparent		
	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density <sup>1</sup>	1.33	g/cm <sup>3</sup>	BS 2782
Molding Shrinkage <sup>2</sup>	0.30	%	BS 2782
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress <sup>3</sup> (Yield)	51.2	MPa	BS 2782
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength <sup>4</sup> (23°C)	7.3	kJ/m <sup>2</sup>	BS 2782
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature			
--	71.5	°C	BS 2782 <sup>5</sup>
--	68.0	°C	BS 2782 <sup>6</sup>
Injection	Nominal Value	Unit	
Rear Temperature	150	°C	
Middle Temperature	155	°C	
Front Temperature	160	°C	
Nozzle Temperature	170	°C	
Mold Temperature	25.0	°C	
Injection Pressure	12.0	MPa	
Back Pressure	0.100 to 0.500	MPa	
Screw Speed	50	rpm	
NOTE			
1.	varies with color		

2.	DTM 225
3.	50 mm/min
4.	Notch A
5.	A (10N)
6.	B (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

